PRODUCT SPECIFICATION: aA-COPY (CIE 163)

Nominal grammage, g/m²	80
Basis weight, g/m²	77 – 83
Moisture, %	3.0 - 4.0
Thickness, µm	103 – 110
Surface roughness TS ml/min Surface roughness BS ml/min	60 – 125 90 – 150
Bending stiffness MD, mN Bending stiffness CD, mN	>110 >50
Opacity, %	>94
Brightness, %	108 – 111
CIE Whiteness	161 - 165

The quality specification is to be used for information only and must not be used as a legal document.

The specification refers to an average of a composite sample withdrawn from a lot with random sampling according to ISO 186 : 2002

Testing conditions:
Relative humidity 50%, Temp. 23 ºC ISO 187 : 1990

Testing methods:
Thickness measurement on single sheets ISO 534 : 2011
Surface roughness according to Bendtsen ISO 8791 - 2 : 1990
Bending stiffness according to ISO 2493-1 : 2010
Opacity according to ISO 2471 : 2008
D65-Brightness according to ISO 2470-2 : 2008
CIE Whiteness according to ISO 11475 : 2004